

1. Scope

This specification is applied to Multilayer Ceramic Chip Capacitor (MLCC) for use in electric equipment for the voltage is ranging from 2.5V to 75V.

The series suitable for general electrics circuit, telecommunications, personal computers and peripheral, power circuit and mobile application. **(This product is compliant with the RoHS & HF.)**

2. Parts Number Code

C	1210	X	106	K	025	T
(1)	(2)	(3)	(4)	(5)	(6)	(7)

(1)Product

Product Code	
C	Multilayer Ceramic Chip Capacitor

(2)Chip Size

Code	Length×Width	unit : mm(inch)
1210	3.20× 2.50	(.126× .098)

(3)Temperature Characteristics

Code	Temperature Characteristic	Temperature Range	Temperature Coefficient
X	X7R	-55℃~+125℃	± 15%

(4)Capacitance

unit :pico farads(pF)

Code	Nominal Capacitance (pF)
106	10,000,000.0

※. If there is a decimal point, it shall be expressed by an English capital letter R

(5)Capacitance Tolerance

Code	Tolerance	Nominal Capacitance
K	± 10.0 %	More Than 10 pF

(6)Rated Voltage

Code	Rated Voltage (Vdc)
025	25

(7)Packaging

Code	Type
T	Tape & Reel

3. Nominal Capacitance and Tolerance

3.1 Standard Combination of Nominal Capacitance and Tolerance

Class	Characteristic	Tolerance	Nominal Capacitance
II	X7R	K (± 10.0 %)	E-3, E-6 series

3.2 E series(standard Number)

Standard No.	Application Capacitance											
E- 3	1.0				2.2				4.7			
E- 6	1.0		1.5		2.2		3.3		4.7		6.8	
E-12	1.0	1.2	1.5	1.8	2.2	2.7	3.3	3.9	4.7	5.6	6.8	8.2
E-24	1.0	1.2	1.5	1.8	2.2	2.7	3.3	3.9	4.7	5.6	6.8	8.2
	1.1	1.3	1.6	2.0	2.4	3.0	3.6	4.3	5.1	6.2	7.5	9.1

4. Operation Temperature Range

Class	Characteristic	Temperature Range	Reference Temp.
II	X7R (X)	-55℃ ~ +125℃	25℃

5. Storage Condition


Storage Temperature : 5 to 40℃

Relative Humidity : 20 to 70 %

Storage Time : 12 months max.


6. Dimensions

6.1 Configuration and Dimension :






Unit:mm					
TYPE	L	W	T	B (min)	BW (min)
1210	3.20± 0.30	2.50± 0.20	2.00± 0.20	1.60	0.30

6.2 Termination Type :



7. Performance

No.	Item		Specification			Test Condition						
1	Visual		No abnormal exterior appearance			Visual Inspection						
2	Dimension		See Page 2			Visual Inspection						
3	Insulation Resistance		500/C Ω min.			Applied Voltage: Rated Voltage Charge Time : 60±5 sec. Charge-Discharge current shall be less than 50mA current.						
4	Capacitance	Class II	Within The Specified Tolerance			Class II : <table><tr><th colspan="2">Frequency</th><th>Voltage</th></tr><tr><td>X7R</td><td>1KHz±10%</td><td>*1.0±0.2Vrms or 0.5±0.2Vrms</td></tr></table> Perform a heat temperature at 150±5℃ for 30min then place room temp. for 24±2hr.	Frequency		Voltage	X7R	1KHz±10%	*1.0±0.2Vrms or 0.5±0.2Vrms
Frequency		Voltage										
X7R	1KHz±10%	*1.0±0.2Vrms or 0.5±0.2Vrms										
5	D.F.	Class II	X7R: 10% max.									
6	Withstanding Voltage		No dielectric breakdown or mechanical breakdown			250% of the rated voltage for 1~5 sec. charge/discharge Current is less than 50mA.						
7	Temperature Capacitance Coefficient	Class II	Char. X7R	Temp. Range -55℃ ~+125℃	Cap. Change(%) ± 15%	Class II : $\frac{C2 - C1}{C1} \times 100\%$ C1:Capacitance At Standard Temperature(25℃) C2: Capacitance At Test Temperature under 1.0Vrms.						
8	Adhesive Strength Of Termination		No indication of peeling shall occur on the terminal electrode.			Pull force shall be applied for 10± 1 second. 0201----2N(≒ 0.2 Kg·f) 0402/0603----5N(≒ 0.5 Kg·f) ≥ 0805----10N(≒ 1.0 Kg·f) 						
9	Resistance to Flexure of Substrate	Appear- ance	No mechanical damage or capacitance change more than the following table.			The board shall be bend 1.0mm with a rate of 1.0 mm/sec. The duration of the applied forces shall be 10 ± 1sec 						
		C-Meter	Capacitance Change									
			Char.	Cap. Change								
			X7R (X)	≤ ± 12.5% of initial value								

No.	Item		Specification		Test Condition															
10	Solderability		More than 90% of the terminal surface is to be soldered newly, so metal part does not come out or dissolve. 		Solder Temperature : 245± 5℃ Dip Time : 5 ± 0.5sec Immersing Speed : 25±10% mm/s Solder : Lead Free Solder Flux :Rosin Preheat : At 80~120 ℃ for 10~30sec.															
11	Resistance To Soldering Heat	Appear- ance	No mechanical damage shall occur.		Class II capacitor shall be set for 48±4 hours at room temperature after one hour heat treatment at 150 +0/-10℃ before initial measure. Preheat : at 150± 10℃ for 60~120sec. Dip : solder temperature of 260± 5℃ Dip Time : 10 ± 1sec. Immersing Speed : 25±10% mm/s Flux :Rosin Measure at room temperature after cooling for Class II : 48 ± 4 Hours															
		Capacit- ance	Class II X7R	≤ ±7.5% of initial value																
		D.F. Class II	X7R: 10% max.																	
		Insulation Resistance	To satisfy the specified initial value																	
12	Tempera- ture Cycle	Appear- ance	No mechanical damage shall occur.		Class II capacitor shall be set for 48±4 hours at room temperature after one hour heat treatment at 150 +0/-10℃ before initial measure. Capacitor shall be subjected to five cycles of the temperature cycle as following: <table border="1" data-bbox="1003 1041 1468 1220"><thead><tr><th>Step</th><th>Temp.(℃)</th><th>Time(min)</th></tr></thead><tbody><tr><td>1</td><td>Min Rated Temp. +0/-3</td><td>30</td></tr><tr><td>2</td><td>25</td><td>3</td></tr><tr><td>3</td><td>Max Rated Temp. +3/-0</td><td>30</td></tr><tr><td>4</td><td>25</td><td>3</td></tr></tbody></table> Measure at room temperature after cooling for Class II : 48 ± 4 Hours	Step	Temp.(℃)	Time(min)	1	Min Rated Temp. +0/-3	30	2	25	3	3	Max Rated Temp. +3/-0	30	4	25	3
		Step	Temp.(℃)	Time(min)																
		1	Min Rated Temp. +0/-3	30																
		2	25	3																
3	Max Rated Temp. +3/-0	30																		
4	25	3																		
Capacit- ance	Class II X7R	≤ ±7.5% of initial value																		
D.F. Class II	X7R: 10% max.																			
Insulation Resistance	To satisfy the specified initial value																			
13	Humidity	Appear- ance	No mechanical damage shall occur.		Class II capacitor shall be set for 48± 4 hours at room temperature after one hour heat treatment at 150 +0/-10 ℃ before initial measure. Temperature : 40± 2℃ Relative Humidity : 90 ~ 95%RH Test Time : 500 Hrs Max. Measure at room temperature after cooling for Class II : 48 ± 4 Hours															
		Capacit- ance	Characteristic	Cap. Change																
			X7R	≤ ±12.5% of initial value																
		D.F. Class II	X7R: 20% max.																	
Insulation Resistance	50/C Ω min.																			

No.	Item	Specification	Test Condition
14	Humidity Load	Appearance	Class II capacitors applied DC voltage of the rated voltage is applied for one hour at maximum operation temperature $\pm 3^{\circ}\text{C}$ then shall be set for 48 ± 4 hours at room temperature and the initial measurement shall be conducted. Applied Voltage : Rated Voltage Temperature : $40 \pm 2^{\circ}\text{C}$ Relative Humidity : 90 ~ 95%RH Test Time : 500 Hrs Max. Current Applied : 50 mA Max. Class II capacitor for $\text{Cap} \geq 103(10\text{nF})$ shall be set for 24 ± 2 hours at room temperature after one hour heat treatment at $150 \pm 0/-10^{\circ}\text{C}$ before final measure. Class II capacitor for $\text{Cap} < 103(10\text{nF})$ Measure at room temperature after cooling for 48 ± 4 Hours.
		Capacitance	
		Characteristic	
		Cap. Change	
15	High Temperature Load (Life Test)	X7R	The capacitors applied DC testing voltage is applied for one hour at maximum operation temperature $\pm 3^{\circ}\text{C}$ then shall be set for 48 ± 4 hours at room temperature and the initial measurement shall be conducted. Applied Voltage: Rated Voltage Temperature: max. operation temperature Test Time : 1000 Hrs Max. Current Applied : 50mA Max Class II capacitor for $\text{Cap} \geq 103(10\text{nF})$ shall be set for 24 ± 2 hours at room temperature after one hour heat treatment at $150 \pm 0/-10^{\circ}\text{C}$ before final measure. Class II capacitor for $\text{Cap} < 103(10\text{nF})$ Measure at room temperature after cooling for 48 ± 4 Hours.
		Capacitance	
		Characteristic	
		Cap. Change	
16	Vibration	X7R	Solder the capacitor on P.C. board. Vibrate the capacitor with amplitude of 1.5mm P-P changing the frequencies from 10Hz to 55Hz and back to 10Hz in about 1 min. Repeat this for 2 hours each in 3 perpendicular directions.
		Capacitance	
		Characteristic	
		Cap. Change	
14	Humidity Load	D.F. Class II	Class II capacitors applied DC voltage of the rated voltage is applied for one hour at maximum operation temperature $\pm 3^{\circ}\text{C}$ then shall be set for 48 ± 4 hours at room temperature and the initial measurement shall be conducted. Applied Voltage : Rated Voltage Temperature : $40 \pm 2^{\circ}\text{C}$ Relative Humidity : 90 ~ 95%RH Test Time : 500 Hrs Max. Current Applied : 50 mA Max. Class II capacitor for $\text{Cap} \geq 103(10\text{nF})$ shall be set for 24 ± 2 hours at room temperature after one hour heat treatment at $150 \pm 0/-10^{\circ}\text{C}$ before final measure. Class II capacitor for $\text{Cap} < 103(10\text{nF})$ Measure at room temperature after cooling for 48 ± 4 Hours.
		Insulation Resistance	
		Characteristic	
		Cap. Change	
15	High Temperature Load (Life Test)	X7R	The capacitors applied DC testing voltage is applied for one hour at maximum operation temperature $\pm 3^{\circ}\text{C}$ then shall be set for 48 ± 4 hours at room temperature and the initial measurement shall be conducted. Applied Voltage: Rated Voltage Temperature: max. operation temperature Test Time : 1000 Hrs Max. Current Applied : 50mA Max Class II capacitor for $\text{Cap} \geq 103(10\text{nF})$ shall be set for 24 ± 2 hours at room temperature after one hour heat treatment at $150 \pm 0/-10^{\circ}\text{C}$ before final measure. Class II capacitor for $\text{Cap} < 103(10\text{nF})$ Measure at room temperature after cooling for 48 ± 4 Hours.
		Capacitance	
		Characteristic	
		Cap. Change	
16	Vibration	X7R	Solder the capacitor on P.C. board. Vibrate the capacitor with amplitude of 1.5mm P-P changing the frequencies from 10Hz to 55Hz and back to 10Hz in about 1 min. Repeat this for 2 hours each in 3 perpendicular directions.
		Capacitance	
		Characteristic	
		Cap. Change	
14	Humidity Load	D.F. Class II	Class II capacitors applied DC voltage of the rated voltage is applied for one hour at maximum operation temperature $\pm 3^{\circ}\text{C}$ then shall be set for 48 ± 4 hours at room temperature and the initial measurement shall be conducted. Applied Voltage : Rated Voltage Temperature : $40 \pm 2^{\circ}\text{C}$ Relative Humidity : 90 ~ 95%RH Test Time : 500 Hrs Max. Current Applied : 50 mA Max. Class II capacitor for $\text{Cap} \geq 103(10\text{nF})$ shall be set for 24 ± 2 hours at room temperature after one hour heat treatment at $150 \pm 0/-10^{\circ}\text{C}$ before final measure. Class II capacitor for $\text{Cap} < 103(10\text{nF})$ Measure at room temperature after cooling for 48 ± 4 Hours.
		Insulation Resistance	
		Characteristic	
		Cap. Change	
15	High Temperature Load (Life Test)	X7R	The capacitors applied DC testing voltage is applied for one hour at maximum operation temperature $\pm 3^{\circ}\text{C}$ then shall be set for 48 ± 4 hours at room temperature and the initial measurement shall be conducted. Applied Voltage: Rated Voltage Temperature: max. operation temperature Test Time : 1000 Hrs Max. Current Applied : 50mA Max Class II capacitor for $\text{Cap} \geq 103(10\text{nF})$ shall be set for 24 ± 2 hours at room temperature after one hour heat treatment at $150 \pm 0/-10^{\circ}\text{C}$ before final measure. Class II capacitor for $\text{Cap} < 103(10\text{nF})$ Measure at room temperature after cooling for 48 ± 4 Hours.
		Capacitance	
		Characteristic	
		Cap. Change	
16	Vibration	X7R	Solder the capacitor on P.C. board. Vibrate the capacitor with amplitude of 1.5mm P-P changing the frequencies from 10Hz to 55Hz and back to 10Hz in about 1 min. Repeat this for 2 hours each in 3 perpendicular directions.
		Capacitance	
		Characteristic	
		Cap. Change	

When operating at temperature range from 100°C to 125°C, the operation shall be carried out at a derating voltage or less as shown below

Must derating conditions on voltage and temperature




Fig.1

P.C. Board for Bending Strength Test





Fig.2

Test Substrate



Unit:mm


Type	A	B	C
0201	0.2	0.9	0.4
0402	0.5	1.5	0.6
0603	1.0	3.0	1.0
0805	1.2	4.0	1.6
1206	2.2	5.0	2.0
1210	2.2	5.0	2.9
1808	3.5	7.0	2.5
1812	3.5	7.0	3.7
2208	4.5	8.0	2.5
2211	4.5	8.0	3.0
2220	4.5	8.0	5.6

8. Packing

8.1 Bulk Packing

According to customer request.

8.2 Chip Capacitors Tape Packing



8.3 Material And Quantity

Tape	0201	0402	0603/0805	
Material	$T \leq 0.39\text{mm}$	$T \leq 0.70\text{mm}$	$T \leq 1.00\text{mm}$	$T > 1.00\text{mm}$
Paper	15,000 pcs/Reel	10,000 pcs/Reel	4,000 pcs/Reel	NA
Plastic	NA	NA	NA	3,000 pcs/Reel

Tape	1206		
Material	$T \leq 1.00\text{mm}$	$1.00\text{mm} < T \leq 1.25\text{mm}$	$T > 1.25\text{mm}$
Paper	4,000 pcs/Reel	NA	NA
Plastic	NA	3,000 pcs/Reel	2,000 pcs/Reel

Tape	1808/1210		
Material	$T \leq 1.25\text{mm}$	$1.25\text{mm} < T \leq 2.40\text{mm}$	$T > 2.40\text{mm}$
Paper	NA	NA	NA
Plastic	3,000 pcs/Reel	1,000/2,000 pcs/Reel	500/700/1,000 pcs/Reel

Tape	1812/2211/2220		1825/2225		2208
Material	$T \leq 2.20\text{mm}$	$T > 2.20\text{mm}$	$T \leq 2.20\text{mm}$	$T > 2.20\text{mm}$	$T \leq 2.20\text{mm}$
Paper	NA	NA	NA	NA	NA
Plastic	1,000 pcs/Reel	700 pcs/Reel	700 pcs/Reel	400 pcs/Reel	1,000 pcs/Reel


NA : Not Available

8.4 Cover Tape Reel Off Force


8.4.1 Peel-Off Force

$$5 \text{ g} \cdot \text{f} \leq \text{Peel-Off Force} \leq 70 \text{ g} \cdot \text{f}$$

8.4.2 Measure Method



8.5 Paper Tape




Unit:mm

TYPE	A	B	C	D	E
0201	0.37± 0.1	0.67± 0.1	4.00± 0.1	2.00± 0.05	2.00± 0.1
0402	0.61± 0.1	1.20± 0.1			4.00± 0.1
0603	1.10± 0.2	1.90± 0.2			
0805	1.50± 0.2	2.30± 0.2			
1206	1.90± 0.2	3.50± 0.2			
1210	2.90± 0.2	3.60± 0.2			

TYPE	F	G	H	I	t
0201	1.75± 0.10	3.50± 0.05	8.0± 0.30	φ 1.50 +0.10/-0	1.10 max.
0402					
0603					
0805					
1206					
1210					

8.6 Plastic Tape




Unit:mm

Type	A	B	C	D	E	F	
0805	1.5±0.2	2.3±0.2	4.0± 0.1	2.0± 0.05	4.0± 0.1	1.75± 0.1	
1206	1.9±0.2	3.5±0.2					
1210	2.9±0.2	3.6±0.2					
	2.95±0.2	3.65±0.2					
1808	2.5±0.2	4.9±0.2		2.0± 0.05	8.0± 0.1		
1812	3.6±0.2	4.9±0.2			4.0± 0.1		
1825	6.9±0.2	4.9±0.2					8.0± 0.1
2208	2.5±0.2	6.1±0.2					
2211	3.2±0.2	6.1±0.2					
2220	5.4±0.2	6.1±0.2					
2225	6.9±0.2	6.1±0.2					

Type	G	H	I	J	t	O
0805	3.5± 0.05	8.0± 0.3	φ 1.5+0.1/-0	3.0 max.	0.3 max.	1.0± 0.1
1206					0.35 ± 0.05	NA
1210						
1808	5.5± 0.05	12.0 ± 0.3		4.0 max.	0.3 max.	1.5± 0.1
1812						
1825						
2208						
2211						
2220						
2225						

8.7 Reel Dimensions

Reel Material : Polystyrene



Unit:mm

Type	A	B	C	D	E	W
0201	φ 382 max	φ 50 min	φ 13± 0.5	φ 21± 0.8	2.0±0.5	10± 0.15
0402						
0603						
0805						
1206						
1210						
1808	φ 178±2.0	φ 60±2.0				13±0.3
1812						
1825						
2208						
2211						
2220						
2225						

Precautionary Notes:


1. Storage

Store the capacitors where the temperature and relative humidity don't exceed 40°C and 70%RH. We recommend that the capacitors be used within 12 months from the date of manufacturing. Store the products in the original package and do not open the outer wrapped, polyethylene bag, till just before usage. If it is open, seal it as soon as possible or keep it in a desiccant with a desiccation agent.

2. Construction of Board Pattern

Improper circuit layout and pad/land size may cause excessive or not enough solder amount on the PC board. Not enough solder may create weak joint, and excessive solder may increase the potential of mechanical or thermal cracks on the ceramic capacitor. Therefore we recommend the land size to be as shown in the following table: 2.1

Size and recommend land dimensions for reflow soldering




EIA Code	Chip (mm)		Land (mm)				
	L	W	A	B	C	D	E
0201	0.60	0.30	0.2~0.3	0.2~0.4	0.2~0.4	--	--
0402	1.00	0.50	0.3~0.5	0.3~0.5	0.4~0.6	--	--
0603	1.60	0.80	0.4~0.6	0.6~0.7	0.6~0.8	--	--
0805	2.00	1.25	0.7~0.9	0.6~0.8	0.8~1.1	--	--
1206	3.20	1.60	2.2~2.4	0.8~0.9	1.0~1.4	1.0~2.0	3.2~3.7
1210	3.20	2.50	2.2~2.4	1.0~1.2	1.8~2.3	1.0~2.0	4.1~4.6
1808	4.60	2.00	2.8~3.4	1.8~2.0	1.5~1.8	1.0~2.8	3.6~4.1
1812	4.60	3.20	2.8~3.4	1.8~2.0	2.3~3.0	1.0~2.8	4.8~5.3
1825	4.60	6.35	2.8~3.4	1.8~2.0	5.1~5.8	1.0~4.0	7.1~8.3
2208	5.70	2.00	4.0~4.6	2.0~2.2	1.5~1.8	1.0~4.0	3.6~4.1
2211	5.70	2.80	4.0~4.6	2.0~2.2	2.0~2.6	1.0~4.0	4.4~4.9
2220	5.70	5.00	4.0~4.6	2.0~2.2	3.5~4.8	1.0~4.0	6.6~7.1
2225	5.70	6.35	4.0~4.6	2.0~2.2	5.1~5.8	1.0~4.0	7.1~8.3

2.2 Mechanical strength varies according to location of chip capacitors on the P.C. board.







Design layout of components on the PC board such a way to minimize the stress imposed on the components, upon flexure of the boards in depanelization or other processes.

Component layout close to the edge of the board or the "depanelization line" is not recommended.

Susceptibility to stress is in the order of: a>b>c and d>e




2.3 Layout Recommendation

Example	Use of Common Solder Land	Solder With Chassis	Use of Common Solder Land With Other SMD
Need to Avoid			
Recommendation		 $\alpha > \beta$	


3. Mounting

3.1 Sometimes crack is caused by the impact load due to suction nozzle in pick and place operation.

In pick and place operation, if the low dead point is too low, excessive stress is applied to component. This may cause cracks in the ceramic capacitor, therefore it is required to move low dead point of a suction nozzle to the higher level to minimize the board warp age and stress on the components. Nozzle pressure is typically adjusted to 1N to 3N (static load) during the pick and place operation.



3.2 Amount of Adhesive



Example : 0805 & 1206


a	0.2mm min.
b	70 ~ 100 μ m
c	Do not touch the solder land

4. Soldering

4.1. Wave Soldering

Most of components are wave soldered with solder at Peak Temperature.. Adequate care must be taken to prevent the potential of thermal cracks on the ceramic capacitors. Refer to the soldering methods below for optimum soldering benefits.

Recommend flow soldering temperature Profile



Soldering Method	Peak Temp.(°C) / Duration (sec)
1206/0805/0603	$\Delta T \leq 100 \sim 150^{\circ}\text{C}$ max.
Pb-Sn Solder	250°C (max.) / 3sec(max.)
Lead Free Solder	260°C (max.) / 5sec(max.)

Recommended solder compositions

Sn-37Pb (Pb - Sn Solder)

Sn-3.0Ag-0.5Cu (Lead Free Solder)

Wave Soldering is not recommended For Coating Products

To optimize the result of soldering, proper preheating is essential:

- 1) Preheat temperature is too low
 - a. Flux flows to easily
 - b. Possibility of thermal cracks
- 2) Preheat temperature is too high
 - a. Flux deteriorates even when oxide film is removed
 - b. Causes warping of circuit board
 - c. Loss of reliability in chip and other components


Cooling Condition:

Natural cooling using air is recommended. If the chips are dipped into a solvent for cleaning, the temperature difference (ΔT) between the solvent and the chips must be less than 100°C.

4.2 Reflow Soldering

Preheat and gradual increase in temperature to the reflow temperature is recommended to decrease the potential of thermal crack on the components. The recommended heating rate depends on the size of component, however it should not exceed 3°C/Sec.

Recommend reflow profile for Lead-Free soldering temperature Profile (J-STD-020E)



Soldering Method	Change in Temp.(°C)
1206 and Under	$\Delta T \leq 190^{\circ}\text{C}$
1210 and Over	$\Delta T \leq 130^{\circ}\text{C}$


※ The cycles of soldering : Three times (max.)

Maximum Ramp-up = 3°C/Sec.

Maximum Ramp-down Rate = 6°C/Sec.

4.3 Hand Soldering

Sudden temperature change in components, results in a temperature gradient recommended in the following table, and therefore may cause internal thermal cracks in the components. In general a hand soldering method is not recommended unless proper preheating and handling practices have been taken. Care must also be taken not to touch the ceramic body of the capacitor with the tip of solder iron.




Soldering Method	Change in Temp.(°C)
1206 and Under	$\Delta T \leq 150^{\circ}\text{C}$
1210 and Over	$\Delta T \leq 130^{\circ}\text{C}$

How to Solder Repair by Solder Iron


- 1) Selection of the soldering iron tip
The required temperature of solder iron for any type of repair depends on the type of the tip, the substrate material, and the solder land size.
- 2) recommended solder iron condition
 - a.) Preheating Condition : Board and components should be preheated sufficiently at 150°C or over, and soldering should be conducted with soldering iron as boards and components are maintained at sufficient temperatures.
 - b.) Soldering iron power shall not exceed 30 W.
 - c.) Soldering iron tip diameter shall not exceed 3mm.
 - d.) Temperature of iron tip shall not exceed 350°C to perform the process within 5 seconds.
(refer to MIL-STD-202G)
 - f.) Do not touch the ceramic body with the tip of solder iron. Direct contact of the soldering iron tip to ceramic body may cause thermal cracks.
 - g.) After soldering operation, let the products cool down gradually in the room temperature.

5. Handling after chip mounted

5.1 Proper handling is recommended, since excessive bending and twist of the board, depends on the orientation of the chip on the board, may induce mechanical stress and cause internal crack in the capacitor.



5.2 There is a potential of crack if board is warped due to excessive load by check pin





5.3 Mechanical stress due to warping and torsion.


- (a) Crack occurrence ratio will be increased by manual separation.
- (b) Crack occurrence ratio will be increased by tensile force , rather than compressive force.

× :Tensile Stress

○ :Compressive Stress




Capacitor Stress Analysis




6. Handling of Loose Chip Capacitor

6.1 If dropped the chip capacitor may crack.



6.2 In piling and stacking of the P.C. boards after mounting for storage or handling, the corner of the P.C. board may hit the chip capacitor mounted on another board to cause crack.



7. Safekeeping condition and period

For safekeeping of the products, we recommend to keep the storage temperature between +5 to +40 °C and under humidity of 20 to 70% RH. The shelf life of capacitors is 12 months.